



BLOC'ROUILLE

RUST PASSIVATOR

ANTI-CORROSION PROTECTION

DEFINITION

Very powerful converter and passivator of rust

ADVANTAGES

It combines with rust to form a hard black, stable compound that adheres to iron.
It allows corroded surfaces to be repainted.
It acts at room temperature.
It enables treated parts to be exposed to inclement weather.
Recognised by automobile manufacturers.
More effective and more concentrated than the average commercial product.

APPLICATION FIELDS

Transport, marine, etc.
Mechanical, mechanical welding, etc.
All sectors using metallic parts in oxidising or salty atmospheres, or where they must be protected from rust.

TECHNICAL CHARACTERISTICS

Aspect thixotropic liquid
Colour cream
Density at 20°C (ASTM D4052) 1
pH of concentrated product 2.5
Coverage 10-15 m²/L
Non-volatile matter 24%
Non-flammable liquid

TECHNICAL CHARACTERISTICS OF THE FILM

Aspect matt black
Drying time (dust-free) 15 min
 Dry 30 min
 Hard 12 h
Salt Spray Test >150 h on rusted plate, according to ASTM B 117

COMPLIES with PMUC specifications: halogen content <200 ppm

1/2

Manufacturing site and registered office

Parc Industriel de la Plaine de l'Ain - 225 allée des Cèdres - 01150 Saint-Vulbas - FRANCE
Tél. +33 (0)4 74 40 20 25 - Fax +33 (0)4 74 40 20 26 - www.orapi-maintenance.com

INSTRUCTIONS FOR USE

Before applying BLOC'ROUILLE to rusted surfaces, to obtain the best results, it is necessary to:

1. Brush the area to remove loose rust particles
2. If needed, degrease the surface with a solvent that does not damage paint (ORASOLV B30 for example)
3. Apply BLOC'ROUILLE after the solvent has dried completely.
The treated surface will get progressively darker. If the result is uneven, wait an hour, and then apply a second coat
4. Allow to dry 16-24 hours before painting
Apply using a brush, or by spraying For this, the material must be stainless steel, plastic or aluminium

PACKAGING

2954 R3	500 ml oil can	x 12
2954 J1	5 kg jerry-can	x 4
2954 U2	200 kg drum	x 1

2/2

Manufacturing site and registered office

Parc Industriel de la Plaine de l'Ain - 225 allée des Cèdres - 01150 Saint-Vulbas - FRANCE
Tél. +33 (0)4 74 40 20 25 - Fax +33 (0)4 74 40 20 26 - www.orapi-maintenance.com

ORAPI® cannot be expected to know all applications in which its products are used or their conditions of use. ORAPI® shall not be held responsible: for the suitability of its products for a given use or specific purpose, for the methods of application over which it has no control. The information contained in this technical data sheet can on no account be a substitute for the preliminary tests which are essential and which must be carried out in order to check the suitability of the product to each intended application. The user of the product described in this technical data sheet is solely responsible for all measures required to protect people and property from hazards that may arise from the implementation and/or use of this product. Therefore, ORAPI® renounces any implicit or explicit guarantees, including guarantees relating to marketability or suitability for a certain purpose, resulting from the sale or use of its products. In particular, ORAPI® renounces any claims for incidental or consequential damages whatsoever, including financial operating losses.