



PROTOR PL

PEELABLE PROTECTIVE VARNISH RED or COLOURLESS

FAST DRYING and RESISTANT FILM

DEFINITION

Red or colourless peelable protective varnish designed to protect:

Indoors and outdoors:

- parts against rust;
- spray painting booths against splattering on floors and walls;
- cutting tools during storage and transport;
- equipment and materials against radioactive contamination;
- floors and walls in industrial environments against various contaminants (grease, oil, dust etc.)
- against dust during the disposal of certain types of waste (cement, asbestos etc.)

ADVANTAGES

Easily applied (tools can be rinsed with an ORASOLV O - 514 type solvent).
Comes off quickly and easily.
The film protects polished aluminium and steel sheets against scratches and corrosion.
Compatible with ferrous and non-ferrous metal parts.
Apply at room temperature.
Extremely resistant and elastic peelable film, peels off easily.
Indoor protection: 12 months minimum.
Facilitates tool handling as cutting edges are protected.
Can be used on parts stored outdoors.
Protection against rust for shipment.

APPLICATION FIELDS

Advised for the protection of

- polished machined parts, rolling mill cylinders, tools, etc.;
- walls and windows of spray painting booths or parts not to be painted (see photos 3a, 3b and 3c)
- Store windows to hide the inside of the shop (works), against dust from waste etc.
- metal rods, T-joints, U-shaped guide rails for storage and maritime transport (in containers)
- automotive or bicycle parts, metal furniture, simple moulds for plastics etc.
- new tools against rust, scratches and knocks - photos 1a and 2a.
- material and equipment in contaminated areas of nuclear power plants.
- lifting machines and handling equipment against various projections (acids, paint etc.)

**- 1/2 -
Head office**

Parc Industriel de la Plaine de l'Ain - 225 allée des Cèdres - 01150 Saint-Vulbas - FRANCE
Tel. +33 (0)4 74 40 20 25 - Fax +33 (0)4 74 40 20 26 www.orapi-maintenance.com



Photo 1a



Photo 2a



Photo 3a



Photo 3b



Photo 3c

Non-contractual photographs taken with our 969 product.

TECHNICAL CHARACTERISTICS

Aspect	liquid
Colour	red 967 or colourless 968
Flash point (ASTM D56)	21°C
Coverage	> 8 m ² /litre approx.
Coating thickness (spray gun)	Approx. 0.1 mm
Density	0.900
Drying time	Approx. 30 minutes

INSTRUCTIONS FOR USE

Shake gently before using.
 This product can be applied by immersion, with a brush or sprayed using a spray gun (with recommended pressure of 40-60 psi, approx. 2-4 bars).
 Application of two thick layers is highly recommended for easier removal.
 Use on clean and preferably smooth surfaces, which makes peeling easier and prevents micro-tears in the film.
 Drying time can be shortened by air blowing or using a drying oven at 40°C.
 All tools can be easily rinsed with ORASOLV O- 514.

PACKAGING

RED			COLOURLESS		
1 kg container	Ref. 2967 i2	x 12	1 kg container	Ref. 2968 i2	x 12
20 kg drum	Ref. 2967 O1	x 1	5 kg bucket	Ref. 2968 S1	x 4

- 2/2 -
Head office

Parc Industriel de la Plaine de l'Ain - 225 allée des Cèdres - 01150 Saint-Vulbas - FRANCE
 Tel. +33 (0)4 74 40 20 25 - Fax +33 (0)4 74 40 20 26 www.orapi-maintenance.com

ORAPI® cannot know about every application for which the products are used nor their conditions of use. ORAPI® shall not be held responsible: for the suitability of its products for a given use or specific purpose, for the methods of application over which it has no control. The information contained here can on no account be a substitute for the preliminary tests which are essential and which must be carried out in order to check the suitability of the product to each specific case. The user of the product described in this technical data sheet is solely responsible for all measures required to protect people and property from hazards that may arise from the implementation and/or use of this product. Therefore, ORAPI® renounces any implicit or explicit guarantees, including guarantees relating to marketability or suitability for a certain purpose, resulting from the sale or use of its products. In particular, ORAPI® renounces any claims for incidental or consequential damages whatsoever, including financial operating losses.