

Technical Datasheet

Elecolit[®] 414

Product Description

Panacol Elecolit[®] adhesives are single or two-component adhesives. They are mostly based on epoxy resin and can be cured at room temperature or by exposure of heat. Elecolit[®] adhesives are electrically and / or thermally conductive adhesives which are designed for potting, bonding or contacting of conductors.

Elecolit[®] 414 is a single component silver-filled, electrical conductive coating substance, that hardens into a flexible, chemical resistant, elastic film.

When used with common plastics Elecolit[®] 414 has outstanding bonding properties (among others on polyamide). It is, for example, used in foils for exterior mirrors, that are heated. After prolonged storage, the product has to be homogenized because the silver naturally sediments in the low-viscosity resin.

Thawing time before usage will be approx. 1h for 30cc cartridges. Try to avoid condensation during thawing process. Once Elecolit[®] 414 is thawed do not re-freeze again. Elecolit[®] 414 must be stored vertically with cartridge tip downwards.

Curing Properties

The product is a one-component adhesive and cures under exposure to heat. Possible curing temperatures are listed in the table below.

Thermal curing	[min]
Time at 70°C	16
Time at 125°C	8
Time at 150°C	5

The curing times given are guidelines. They refer to the curing of 2 g of adhesive. The heating up of the joining members are not taken into account.

The final strength of the adhesive is reached at the earliest after 24 h.

Technical Data

Resin	polyester
Appearance	grey
Filler	silver flakes
Filler – weight [%]	87
Particle size D95 [µm]	16

Technical Datasheet

Elecolit[®] 414

Uncured material

Viscosity [mPas] (Brookfield LVT, 25°C, Sp 4 , 6 rpm) <i>PE-Norm 001</i>	20 000 - 25 000
Density [g/cm ³] <i>PE-Norm 004</i>	2,84
Flash point [°C] <i>PE-Norm 050</i>	>58
Work life time [h] <i>at room temperature</i>	6

Cured material

Hardness shore D <i>PE-Norm 006</i>	55
Temperature resistance [°C]	-55 - 200

Glass transition temperature DSC [°C] <i>PE-Norm 009</i>	20 - 25
---	---------

Volume resistivity [Ohm*cm] <i>PE-Norm 040</i>	5,E-05
---	--------

Transport/Storage/Shelf Life

Trading unit	Transport	Storage	Shelf-life*
cartridges	-20°C	-20°C	At delivery min. 6 months, max. 12 months
Other packages	at room temperature max. 25°C	0°C - 10°C	

***Store in original, unopened containers!**

Instructions for Use

Surface preparation

The surfaces to be bonded should be free of dust, oil, grease or other dirt in order to obtain an optimal and reproducible bond.

For cleaning we recommend the cleaner IP[®] Panacol. Substrates with low surface energy (e.g. polyethylene, polypropylene) must be pretreated in order to achieve sufficient adhesion.

Technical Datasheet

Elecolit[®] 414

Application

Our products are supplied ready to use. Depending on packaging they can be applied by hand directly from the container or semi or fully automatically. When metering low viscosity materials from bottles the adhesive is transported by a diaphragm valve. If help is required, please contact our application engineering department.

Adhesive and substrate may not be cold and must be warmed up to room temperature prior to processing.

For safety information refer to our safety data sheet.

Disclaimer

The product is free of heavy metals, PFOS and Phthalates and is conform to the EU-Directive 2017/2102/EU "RoHS III".

THE VALUES NOTED IN THIS TECHNICAL DATA SHEET ARE TYPICAL PROPERTIES AND ARE NOT MEANT TO BE USED AS PRODUCT SPECIFICATIONS.

The information contained in this data sheet is believed to be accurate and is provided for information only. Panacol makes no representation or warranties of any kind concerning this information. It is the user's responsibility to determine the suitability of this product for any intended use. Panacol does not assume responsibility for test or performance results obtained by the user. The user assumes all risk and liability connected with the use of this product.

The user should adopt such precautions and use guidelines as may be advisable for the protection of property and persons against any hazards that may be involved in this product's handling or use. Panacol specifically disclaims any liability for consequential or incidental damages of any kind arising from the handling or use of this product.

The information contained in this Technical Data Sheet offers no assurance that the product use, application, or process will not infringe on existing patents or licenses of others. Nothing in this Technical Data Sheet transfers or grants license for the use of any patents, trade secrets, intellectual property, or confidential information that is the property of Panacol.

Except as otherwise noted, all trademarks in this document (identified as [®]) are the property of Panacol.