

Technical Datasheet

Vitralit® UV 2115

Product Description

Panacol Vitralit® adhesives are one-component, solvent-free radiation-curing adhesives. The advantages are very short curing times, good adhesion to a variety of substrates, and easy handling. Vitralit® products are used in electronics, medical applications, optics and for fixing parts in general.

Vitralit® UV 2115 is a UV- and light-curing acrylate hybrid system with very good adhesion on many materials. Vitralit® UV 2115 is used for bonding / sealing of plastics as well as glass, metals or FR4 for the protection of sensitive components against mechanical and environmental influences. Vitralit® UV 2115 highly filled, has a low coefficient of linear expansion and low shrinkage. Vitralit® UV 2115 is impact resistant, has a dry surface and is resistant to industrial soldering.

Curing Properties

UV-A	VIS	Thermal curing	Activator curing
✓	✓	-	-

✓ suitable - not suitable

The product cures within seconds with radiation in the UV-A - (320 nm - 390 nm) and visible range (405 nm). For rapid and high quality crosslinking we recommend the UV devices manufactured by Dr. Hoenle AG, which complement our adhesive technology.

UV-curing (Hoenle Discharge lamp, 320-450nm)		
Intensity [mW/cm ²]	Layer thickness [mm]	Time [sec]
60	0,05	2

VIS-curing (Hoenle LED Spot 100, 405nm)		
Intensity [mW/cm ²]	Layer thickness [mm]	Time [sec]
100	0,05	20

To obtain full cure at least one substrate must be transparent to the recommended wavelength. The curing speed will depend on the intensity of light, light source, the exposure time, and the light transmittance of the substrate. Increased mechanical properties are achieved after 12 hours.

Technical Data

Resin	epoxy - acrylate
Appearance	grey
Filler	glass
Filler – weight [%]	35
Particle size Ø [µm]	10

Technical Datasheet

Vitralit® UV 2115

Uncured material

Viskosity [mPas] (Kinexus Rheometer, 25 °C, 33s ⁻¹) <i>PE-Norm 064</i>	20 000 - 30 000
Density [g/cm ³] <i>PE-Norm 004</i>	1,3
Flash point [°C] <i>PE-Norm 050</i>	>100
Refractive index [nD20] <i>PE-Norm 018</i>	1,510

Cured material

Hardness shore D <i>PE-Norm 006</i>	70 - 80
Temperature resistance [°C]	-40 - 150
Shrinkage [%] <i>PE-Norm 031</i>	<2
Water absorption [mass %] <i>PE-Norm 016</i>	<1

Glass transition temperature DSC [°C] <i>PE-Norm 009</i>	50 - 60
Coefficient of thermal expansion [ppm/K] below Tg <i>PE-Norm 017</i>	52
Coefficient of thermal expansion [ppm/K] above Tg <i>PE-Norm 017</i>	280

Dielectric strength [kV/mm]	40
-----------------------------	----

Technical Datasheet

Vitralit® UV 2115

Young's modulus E [MPa] <i>PE-Norm 056</i>	1 345
Tensile strength [MPa] <i>PE-Norm 014</i>	17
Elongation at break [%] <i>PE-Norm 014</i>	5
Lap shear strength (PC/PC) [MPa] <i>PE-Norm 013</i>	7
Lap shear strength (PC/steel) [MPa] <i>PE-Norm 013</i>	7
Lap shear strength (PC/FR4) [MPa] <i>PE-Norm 013</i>	6
Lap shear strength (glass/glass) [MPa] <i>PE-Norm 013</i>	10
Lap shear strength (glass/Al) [MPa] <i>PE-Norm 013</i>	12
Lap shear strength (glass/stainless steel) [MPa] <i>PE-Norm 013</i>	13

Transport/Storage/Shelf Life

Trading unit	Transport	Storage	Shelf-life*
Cartridge	at room temperature	at room temperature	at delivery min. 6 months
Other packages	max. 25°C	max. 25°C	max. 12 months

***Store in original, unopened containers!**

Instructions for Use

Surface preparation

The surfaces to be bonded should be free of dust, oil, grease or other dirt in order to obtain an optimal and reproducible bond.

For cleaning we recommend the cleaner IP® Panacol. Substrates with low surface energy (e.g. polyethylene, polypropylene) must be pretreated in order to achieve sufficient adhesion.

Application

Our products are supplied ready to use. Depending on packaging they can be applied by hand directly from the container or semi or fully automatically. With automated application from the cartridge the adhesive is conveyed by a compressed air-operated displacement plunger via a valve in the needle. When metering low viscosity materials from bottles the adhesive is transported by a diaphragm valve. If help is required, please contact our application engineering department.

Adhesive and substrate may not be cold and must be warmed up to room temperature prior to processing.

After application, bonding of the parts should be done quickly. Vitralit® adhesives cure slowly in daylight. Therefore, we recommend to expose the material to as little light as possible and the use of opaque hose lines and dispensing needles. For safety information refer to our safety data sheet.

Technical Datasheet

Vitralit® UV 2115

Disclaimer

The product is free of PFOS and Phthalates and is conform to the EU-Directive 2017/2102/EU "RoHS III".

THE VALUES NOTED IN THIS TECHNICAL DATA SHEET ARE TYPICAL PROPERTIES AND ARE NOT MEANT TO BE USED AS PRODUCT SPECIFICATIONS.

The information contained in this data sheet is believed to be accurate and is provided for information only. Panacol makes no representation or warranties of any kind concerning this information. It is the user's responsibility to determine the suitability of this product for any intended use. Panacol does not assume responsibility for test or performance results obtained by the user. The user assumes all risk and liability connected with the use of this product.

The user should adopt such precautions and use guidelines as may be advisable for the protection of property and persons against any hazards that may be involved in this product's handling or use. Panacol specifically disclaims any liability for consequential or incidental damages of any kind arising from the handling or use of this product. The information contained in this Technical Data Sheet offers no assurance that the product use, application, or process will not infringe on existing patents or licenses of others. Nothing in this Technical Data Sheet transfers or grants license for the use of any patents, trade secrets, intellectual property, or confidential information that is the property of Panacol.

Except as otherwise noted, all trademarks in this document (identified as ®) are the property of Panacol.